


# F503

## Flame-retardant Tissue Paper Double Sided Tape



### Composition:

---



### Applications:

---

- Punching, bonding of nameplates, membrane switch and automobile accessories with fireproof requirements.
- Interior materials for automobiles, train cars and airplanes.
- For various foam materials such as PU, PE, EPDM, PET.

### Features:

---

- UL94 VTM-0 certified.
- Superior initial adhesion.
- Excellent adhesion to rough surfaces.
- Excellent performance under a wide range of temperature condition.
- Low smoke, non-toxic, low burning rate and no dripping during burning.

### Standard Size


- |   |             |
|---|-------------|
| • Total Thickness<br>( without release paper) | 0.12mm      |
| • Liner thickness                             | 0.11mm      |
| • Width                                       | 10mm-1020mm |
| • Length                                      | 50m-500m    |

## Technical Data (average values)

• Backing material	Tissue paper
• Color	White
• Type of adhesive	Acrylic Pressure Sensitive Adhesive
• Temperature resistance range	-20°C-60°C
• Temperature resistance short term	100°C
• Temperature resistance long term	60°C
• Loop tack	≥26#
• Holding power	Up to 180°C for 120 min.

180 Degrees of Peeling Adhesion	
Substrate	Avg. Test Values
Stainless Steel	16N/25mm
ABS	15 N/25mm
PC	20 N/25mm
PE	4 N/25mm
PVC	17 N/25mm
PP	10 N/25mm

Unit:N/25mm  
Sample Width:25mm  
Backing Material: PET film  
Application Condition:  
3 pass back and forth with a  
2.5kg roller  
Peeling Speed: 300mm/min  
Peeling Angle: 180 degree  
Measurement Temperature:  
23°C/65%RH



## Storage:

1. To obtain optimal adhesion, the bonding surface must be dry and clean.
2. The ideal application temperature range is 20°C to 40°C. To apply tape on surface at temperature below 10°C be not recommend, because the adhesive becomes firm to adhere lightly.

**Test Method:** In accordance with GB/T 4851-1998 method.

## Shelf Life:

12 months when stored in original carton at 23°C and 65% relative humidity

## Other:

- Rewinding length commonly used: 55m /roll, and can be processed according to customer demand
- Special carton packaging