


FM701

MOPP Strapping Tape



Composition:



Solvent based Adhesive
MOPP Film

Applications:

- General strapping, used for palletizing, unitizing and bundling.
- Designed for demanding application requirements of appliance industries (including metal office furniture, small appliances, parts, etc.).
- Good for bundling and tying various plastic bags using in bag neck sealer.

Features:


- Transfer-Resistant, delamination Resistant.
- The strapping tape features a very short dwell time until reaching its final adhesive strength.
- High strength film backing resists breaking, abrasion, moisture and scuffs.

Technical Data (average values)


Backing material	MOPP
Total Thickness	0.11mm
Backing Thickness	0.085mm
Color	Blue
Adhesive	Solvent based Adhesive
Width	10mm~1200mm
Length	50m~2500m
Temperature resistance short term	120°C
Temperature resistance long term	80°C
Loop tack	≥15#
Holding power	Up to 120°C for 120 min.
180° Peel Adhesion	7N/25mm
Elongation at break	31%

180°C Peel Adhesion	
Substrate	Avg. Test Values
Stainless Steel	≥13N/25mm
ABS	14.7N/25mm
PC	15N/25mm
PE	5.5N/25mm
PVC	23N/25mm
PP	8N/25mm

Unit:N/25mm
 Sample Width:25mm
 Application Condition:
 3 pass back and forth with a
 2.5kg roller
 Peeling Speed: 300mm/min
 Peeling Angle: 180 degree
 Measurement Temperature:
 23°C/65%RH



Applicable Materials	
Substrate	Level
Stainless Steel	•••
ABS	•••
PC	•••
PE	••
PVC	••••
PP	••



MOPP Strapping Tape shows excellent tack performance to different substrate like this heavy load because of its high tensile strength and holding power.

Storage:

- Please be sure to keep the tape in its box when not using.
- The ideal application temperature range is 20°C to 40°C.
- Keep in a cool and dark place away from direct sunlight.

Test Method:

In accordance with GB/T 4851-1998 method.

Shelf Life:

12 months when stored in original carton at 23° C and 65% relative humidity.

Note:

- Remove all oil, moisture and dirt from the surface of the substrate before applying.
- Make sure the product is suitable for the application (objective and conditions) before attempting to use.

Room 1003-1 , Dahai office building ,
 No.499 Taikang middle road,
 Yinzhou District ,Ningbo City ,
 Zhejiang Province ,China .

Tel. +86 18606581882
 Fax. +0574-88913422
 admin@f6tape.com
<https://f6tape.com/>